

Caster Application - Quick Guide*

Tread Material	Maximum Load	Rollability	Grease/Oil Resistance	Floor Protection	Quiet in Use	Continuous Temp. Operation
Soft Solid Rubber	200 lbs. (90.7 kg.)	Low	Low	High	Yes	-30°F-160°F -34°C-71°C
Neoprene	225 lbs. (102 kg.)	Medium	High	High	Yes	-30°F-180°F -34°C-82°C
Polyurethane	400 lbs. (181 kg.)	High	High	High	No	-30°F-180°F -34°C-82°C
Hi-Temp Phenolic	300 lbs. (136 kg.)	High	High	Medium	No	-50°F-475°F -46°C-246°C
Solid Polyolefin	300 lbs. (136 kg.)	High	High	Low	No	-30°F-180°F -34°C-82°C
Hi-Modulus Rubber	250 lbs. (113 kg.)	High	High	High	Yes	-40°F-180°F -40°C-82°C

TIM CAMPBELL 800-400-7500